

VISCOM - Specialties

Issue date : 05/01/2005
Date last modification : 09/10/2014**01351 RI-1960/50 PVC ULTRADESTRUCTIBLE MATT WHITE ASP WKPE144****Face Material**

Ultradeestructible white cast vinyl.

Type	Cast vinyl
Colour and Finish	Matt white
Weight	100 g/m ² ±10% ISO-536
Thickness	50 µ ±10% ISO 534-80

Adhesive

Permanent adhesive with good initial tack with rapid bond built to ensure destructibility.

Reference	ASP
Type	Permanent acrylic
Min. Appl. Temp.	-5°C
Service Temp.	-10°C to +110°C
Shear	Good
Tack	Medium N/inch ²
Final Adhesion	Very high N/inch

Liner

Type	Siliconised two side PE Kraft
Colour and Finish	White
Weight	144 g/m ² ±10% ISO 536
Thickness	155 µ ±10% ISO 534
Transparency	n.a. % DIN 53 147-64

Applications

Tamperproof labels that once applied has the characteristic of being ultra-destructible when tampered with, because the frontal face tears as pressure is applied.

Printing Methods

Printable in letterpress UV, screenprinting UV and thermal transfer.

Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life6 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.



Ritrama S.p.A.

Via Senatore Simonetta, 24
20867 Caponago (MB) ITALY
e-mail: info@ritrama.com
www.ritrama.com